



LANCO-TEX PU 165

Product Images

Additional Information

Fibre Type of the Base Fabric DIN ISO 2076	DIN ISO 2076
Water Pressure Resistance	>850 mm WS
Weave Style DIN ISO 9354	Plain weave 1/1
Total Mass per Unit Area	<200 g/m ²
Total Mass per Unit Area DIN EN ISO 2286-2	DIN EN 29073-1
Yarn Count DIN EN 1049 Warp	20 Fd/cm
Yarn Count DIN EN 1049 Weft	17 Fd/cm
Titer of Yarn DIN EN ISO 2060 Warp	280 dtex
Titer of Yarn DIN EN ISO 2060 Weft	280 dtex
Fibre Type of the Base Fabric	PES
Colour Fastness - DIN EN ISO 105-B02	EN ISO 105 B02
Colour Fastness	4 - 6
Flame Retardant	Yes
Tear Resistance Warp	>30 N
Tear Resistance Weft	>30 N
Tensile Strength Warp	>900 N/5cm
Tensile Strength Weft	>700 N/5cm
Total Mass per Unit Area	160 g/m ²
Width DIN EN ISO 2286-1	155 cm
Fungicide finish	No
Base Coat	PU
Burning behaviour - Test Standard	DIN 4102 B1
Coating	one side