



LANCO-TEX P 580

Product Images

Additional Information

| | |
|---|-------------------------------------|
| Fibre Type of the Base Fabric DIN ISO 2076 | DIN ISO 2076 |
| Tear Resistance DIN 53363 | DIN 53363 |
| Temperature ranges for use | -30 +70°C |
| min. Extreme temperatures DIN EN 1876 | DIN EN 1876 |
| Tensile Strength DIN EN ISO 1421 | DIN EN ISO 1421 |
| Top Coat | PVC |
| Weave Style DIN ISO 9354 | Plain weave 1/1 |
| Total Mass per Unit Area | 401 - 650 g/m ² |
| Total Mass per Unit Area DIN EN ISO 2286-2 | DIN EN ISO 2286-2 |
| Titer of Yarn DIN EN ISO 2060 Warp | 1100 dtex |
| Titer of Yarn DIN EN ISO 2060 Weft | 1100 dtex |
| Resistance to damage by flexing - DIN 53359 A | 100.000 x no cracks |
| Fibre Type of the Base Fabric | PES |
| Colour Fastness - DIN EN ISO 105-B02 | EN ISO 105 B02 |
| Adhesion EN ISO 2411 Warp | 120 N/5cm |
| Colour Fastness | ≥7 |
| Flame Retardant | Yes |
| Tear Resistance Warp | 250 N |
| Tear Resistance Weft | 250 N |
| Tensile Strength Warp | 2300 N/5m |
| Tensile Strength Weft | 2300 N/5m |
| Total Mass per Unit Area | 580 g/m ² |
| Width DIN EN ISO 2286-1 | 205/218/250 cm |
| Fungicide finish | No |
| Adhesion EN ISO 2411 Weft | 120 N/5cm |
| Base Coat | PVC |
| Burning behaviour - Test Standard | DIN 75200 Burning speed <100 mm/min |
| Coating | both sides |

Colour - LANCO_back

grey, sand, white, yellow, orange, red, blue, green

Colour - RAL_back

1014, 9016, 1003, 2004, 3002, 5002, 6026, 7030