



---

## LANCO-TEX P 780 O

### Product Images

---

## Additional Information

|   |  |
|---|--|
| Fibre Type of the Base Fabric DIN ISO 2076    | DIN ISO 2076   |
| Tear Resistance DIN 53363                     | DIN 53363  |
| Temperature ranges for use                    | -45 +70°C  |
| Tensile Strength DIN EN ISO 1421              | DIN EN ISO 1421  |
| Top Coat                                      | PVC  |
| Weave Style DIN ISO 9354                      | Plain weave 1/1  |
| Total Mass per Unit Area                      | >651 g/m <sup>2</sup>                                    |
| Total Mass per Unit Area DIN EN ISO 2286-2    | DIN EN ISO 2286-2  |
| Titer of Yarn DIN EN ISO 2060 Warp            | 1100 dtex  |
| Titer of Yarn DIN EN ISO 2060 Weft            | 1100 dtex  |
| Resistance to damage by flexing - DIN 53359 A | 100.000 x no cracks                                      |
| Fibre Type of the Base Fabric                 | PET  |
| Colour Fastness - DIN EN ISO 105-B02          | EN ISO 105 B02   |
| Adhesion EN ISO 2411 Warp                     | 100 N/5cm  |
| Colour Fastness                               | >7   |
| Flame Retardant                               | Yes  |
| Tear Resistance Warp                          | 300 N  |
| Tear Resistance Weft                          | 300 N  |
| Tensile Strength Warp                         | 3000 N/5cm   |
| Tensile Strength Weft                         | 3000 N/5cm   |
| Total Mass per Unit Area                      | 780 g/32   |
| Width DIN EN ISO 2286-1                       | 205  |
| Fungicide finish                              | No   |
| Adhesion EN ISO 2411 Weft                     | 100 N/5cm  |
| Base Coat                                     | PVC  |
| Burning behaviour - Test Standard             | UNI 9177 cl. 2, DIN 4102 B1, DIN EN ISO 13501-1 B-s3, d0 |
| Coating                                       | both sides   |